

EOLANE 160

SPECIFICATIONS

MEASURES	UNITS	MEASURES METHODS	GUARANTEED VALUES	
			MINI	MAXI
Density at 15 °C	kg/m ³	ASTM D 4052	805	825
Appearance		Visual	Clear & Bright	
Saybolt Colour		ASTM D 156	+28	
Pensky-Martens Flash Point	°C	ASTM D 93	150	
Aromatic content	ppm	UV		300
Viscosity at 40°C	mm ² /s	ASTM D 445	5,80	6,80
Sulphur Content	ppm	ASTM D 5453		1,0
Water content	ppm	ASTM D 1744		80
Benzene content	ppm	ASTM D 6229		1
Aniline Point (automatic)	°C	ASTM D 611	99,0	103,0
Pour Point	°C	ASTM D 97		0
Initial Point	°C	ASTM D 86	300	
Dry Point	°C	ASTM D 86		370

TYPICAL VALUES

MEASURES	UNITS	MEASURES METHODS	TYPICAL VALUES
Refractive index at 20°C		ASTM D 1218	1,4510

N° spec updated on / SP010112 / 19/09/2011 17:55:31

