

EOLANE 170

SPECIFICATIONS

MEASURES	UNITS	MEASURES METHODS	GUARANTEED VALUES	
			MINI	MAXI
Appearance		Visual	Clear & Bright	
Saybolt Colour		ASTM D 156	+28	
Pensky-Martens Flash Point	°C	ASTM D 93	145	
Aromatic content	ppm	UV		300
Viscosity at 40°C	mm ² /s	ASTM D 445	7,10	8,50
Pour Point	°C	ASTM D 97		-15
Initial Point	°C	ASTM D 86	290	
Dry Point	°C	ASTM D 86		380

TYPICAL VALUES

MEASURES	UNITS	MEASURES METHODS	TYPICAL VALUES
Density at 15 °C	kg/m ³	ASTM D 4052	822
Aniline Point (automatic)	°C	ASTM D 611	101,9
Initial Point	°C	ASTM D 86	295
Dry Point	°C	ASTM D 86	378

N° spec updated on / SP010340 / 19/12/2011

